

*Total Quality. Total Service. Total Satisfaction.*

## T-WALL Lastic

### Description

T-WALL Lastic is a superior quality elastomeric coating.

T-WALL Lastic can be applied directly to concrete, concrete block, EIFS finishes, wood, asbestos shingles and other surfaces without the use of a primer.

T-WALL Lastic provides a waterproof, attractive flat finish.

T-WALL Lastic is designed for permanent flexibility to accept movement from thermal changes and to bridge hair-line cracks.

### Application

Prepare surface by removing any dirt, oils, loose debris or any substance that may interfere with the bond. A dry surface is preferable but a slightly damp surface is acceptable. Previously coated or treated surfaces should have a 4" by 4" test area coated with T-WALL Lastic to test bond. It is advisable to fill any spalled or broken areas of substrate with a suitable patching material. Any cracks greater than an inch should be filled with a paintable grade acrylic caulk and allow to cure 4 hours before beginning coating.

Stir product for one minute with a low speed mixer or manually stick-stir as desired. Do not beat excessive air into the product. Apply T-WALL Lastic by roller, brush or airless sprayer. For airless sprayer, use a reversible tip with a #35 orifice-spraying tip. For roller application, a 1.25-inch nap roller produces good results. The nap thickness can be varied to compensate for the substrate characteristics and the desired appearance.

Thin product with up to 5 ounces of water per gallon if needed. For waterproofing, two 12-15 mil (wet) coats are recommended. When spray applying T-WALL Lastic, it is suggested that the first coat is back-rolled to achieve the best results.

### Coverage

Porous substrates 80-120 sq.ft. / gal /coat

Non-porous substrates 120-150sq.ft. / gal /coat

Two coats are recommended for waterproofing.

### Features

- ◆ Meets VOC, VOS requirements
- ◆ Is easy to apply with water cleanup
- ◆ Does not create a vapor barrier
- ◆ Protects against any weather
- ◆ Is a long lasting and attractive finish
- ◆ Resists dirt pickup
- ◆ Is non-chalking

### Technical Data

Flash point	>200 F Seta	
Density	11.5 lb/gal	
Viscosity	approx 20000 cps	
pH	9.0 - 9.8	
Elongation	>300%	ASTM D412
Actives	> 65%	ASTM D1044
Moisture Vapor Trans.	2.5 perms	ASTM E96
Pigment	non-chalking	UV rated

### Handling and Storage

Do not apply to frozen or saturated surfaces. Do not apply if precipitation is forecast within 8 hours of application. Do not apply if the temperature cannot be maintained above 40 F for 24 hours. Shelf life in closed containers is 12-18 months when stored at 50-100 F. Keep containers sealed and under cover when not in use.

### Maintenance

If T-WALL Lastic becomes dirty or stained, clean with a mild cleaner solution and low-pressure spray rinse. For scars or hard to clean stains, recoat with T-WALL Lastic.

### Precautions

T-WALL Lastic is an alkaline water based material. Do not ingest. Avoid contact with skin and eyes. In case of contact, flush with water. For contact with eyes, get immediate medical attention in addition to flushing. Wear safety glasses and protective clothing. Keep out of reach of children and pets.